

MANTO STONE WOOL and R⁺



It is an unfaced stone wool boards that is produced specially with respect to TS EN 13500 standards. It is utilized at external thermal insulation composite systems for thermal insulation, sound insulation and fire safety purposes.

Application

First of all, the surface to be used in the application should be checked to ensure that it is smooth and dry. If the surface is rough and with scrapes it should be cleaned by brushing. Unevenness, major defects and cracks should be repaired by means of plaster. The boards can be adhered to the surface using cement based fixing mortar by different methods. The boards should be laid down without any gap side by side on the wall surface shortly after spreading fixing mortar over the boards. The adhesive should not be spread near the edges of the board in order to prevent the adhesive getting into the joints. The boards are laid down in an alternating pattern at the facades and the corners. When the fixing mortar is completely dry (approximately after 24 hours) the anchoring process can be started. Special insulation fastening anchors are used which are chosen with respect to the wall properties. Tiled surfaces or surfaces with old plaster are not suitable for anchoring. After anchoring process, reinforced layer is formed. Cement based undercoat plaster is applied to the surface by trowel. Afterwards, an alkali resistant, glass fiber based reinforcement mesh is placed on top by trowel in such a manner that the edges are overlapped by 10 cm. Consequently, second coat plaster is applied on the mesh and the reinforced layer comes to an end. When the reinforced layer is completely dry; permeable, solvent-free decorative cladding material with the desired texture is applied to the reinforced layer using a trowel or roller and the process is completed. Exterior cladding thickness and the quantity to be applied depend on the plaster type. Different surface forms can be achieved on the finishing plaster by different polishing methods. This application is correct in terms of that it removes thermal bridges by insulating wall surfaces as well as it protects the building from atmospheric conditions and prevents physical changes which occur in building components such as expansion or contraction due to temperature change. For the insulation applications of exterior walls from the exterior, using Manto Stone Wool boards provides sound insulation and fire safety as well as thermal insulation.



Thickness (cm)	Width x Length (cm)	Package (m ²)
3	60 x 120	3,60
4	60 x 120	2,88
5	60 x 120	2,16
6	60 x 120	1,44
8	60 x 120	1,44
10	60 x 120	1,44
12	60 x 120	0,72

- Thermal insulation
- Fire safety
- Sound insulation
- Easy to apply



TECHNICAL DATA SHEET

izocam Manto Stone Wool and Manto Stone Wool R⁺

Properties	Symbol	Unit	Description							Tolerance	Standard	
Material	-	-	Stone Wool							-	TS EN 13162	
Material Type	-	-	Manto Stone Wool				Manto Stone Wool R ⁺			-	-	
Density	ρ	kg/m ³	150				130			+/- % 7	-	
Width	w	mm	600							+/-1,5%	TS EN 822	
Length	l	-	1200							+/-2%	TS EN 822	
Thickness	t	mm	30	40	50	60	80	100	120	T5 *	TS EN 823	
Facing	-	-	Unfaced							-	-	
Reaction to fire	-	-	A1							-	TS EN 13501-1	
Squareness	S _b	mm/m	max.5							-	TS EN 824	
Flatness	S _{max}	mm	max.6							-	TS EN 825	
Dimensional Stability	$\Delta\epsilon_d$	%	max.1							-	TS EN 1604	
Declared Thermal Conductivity (10°C)	λ_D	W/mK	0,039				0,037			-	TS EN 12667/12939	
Thermal Resistance	MT	R _D	m ² K/W	0,75	1,00	1,25	1,50	2,05	2,55	3,05	-	TS EN 13162
	MT R ⁺			0,80	1,05	1,35	1,60	2,15	2,70	3,20		
Water Vapor Diffusion Resistance Coefficient **	μ	-	1							-	TS EN 12086	
Pulling Strength	σ_{mt}	kPa	min. 7,5	min. 10			min. 7,5				-	TS EN 1607
Compressive Strength	MT	σ_{10}	kPa	min. 25			min. 30				-	TS EN 826
	MT R ⁺			min. 10			min. 20					
Long Term Water Absorption	W _{lp}	kg/m ²	max. 3							-	TS TS EN ISO 16535	
Short Term Water Absorption	W _p	kg/m ²	max. 1							-	TS TS EN ISO 29767	
Packaging Material	-	-	PE Film							-	-	
Other Information	Manto Stone Wool insulation boards are manufactured regarding to the technical specifications of insulation boards stated in TS EN 13500 for "Mineral wool (stone wool) based external thermal insulation composite systems" and in compliance with TS 901-1 EN 13162 standard.											

* T5: -1% or -1 mm; +3 mm. The biggest value is chosen at minus tolerance, the smallest value is chosen at plus tolerance.

** Literature value.

Safety Reminders for Loading, Unloading, Shipping and Storing

- These operations should be done indoors in case of rainy weather conditions.
- Loading and unloading should be done by (at least) two people.
- Products should be wrapped by a waterproof cover even if the shipping distance is short.
- Products should not be superposed with pallets.
- Products should not be put into upright position.
- Products should not be stepped on and should not be used as steps.
- Products should not be pulled by their package.
- Products should be in packages (10 each) and maximum 6 packages can be superposed.
- Before binding, hard cardboards (minimum 20 x 50 cm) should be put on the corners of packages to protect against possible damages by ropes.
- Storage area should be protected against any wet threats such as rain, float, etc. Indoor spaces should be preferred.
- The packages should be put on the floor with extra care so the corners of the product especially is not damaged by a hit.

Izocam is not responsible for any problem because of misprinting. Izocam, the manufacturer, reserves the right to alter product specifications without prior notice. Izocam also manufactures special products upon request. For your requirements, you are requested to contact our Export Department.

